



INTERCHEM JSC

High Chlorinated Polyethylene (HCPE-H)

Technical Data Sheet

Formula	$(C_2H_4)_n$
CAS Number	9002-86-2

Product Specifications	Value
Viscosity, (Tu-4cup/25), S	40-100
Heating loss , %	0.40
Chlorine content , %	65
Ash , % Fe , %	0
Heating stability, min	20
Heat Decomposition Temperature	120
Dissolved time, min	20

Packaging	• 20 kg polypropylene bag
------------------	---------------------------

Contact us:

E-mail: info@interchemical.ru

Tel.: 8 (812) 611-08-15