



**INTERCHEM JSC**

# Epoxy Resin SE601

## Technical Data Sheet

---

<b>CAS Number</b>	<b>25036-25-3</b>
-------------------	-------------------

---

<b>Product Specifications</b>	<b>Value</b>
Softening Point, °C	65-75 °C
Epoxy Equiv Weight, g/eq	450-500 g/eq
Organic Chloride, eq/100g	≤ 0.0023 eq/100g
Inorganic Chloride, eq/100g	≤ 0.0006 eq/100g
Volatile, %	≤ 0.1 %

---

<b>Packaging</b>	<b>• 25 kg polypropylene bag</b>
------------------	----------------------------------

---

**Contact us:**

***E-mail:* [info@interchemical.ru](mailto:info@interchemical.ru)**

***Tel.:* 8 (812) 611-08-15**